

Niklakett Premium Fashion

by B & B

Magnificent, luxurious & sensuous
Niklakett Premium Fashion – the superior one

High gloss embossed label paper, high wet strength and alkali resistant. High wet opacity. High climate stability. Highest printing and labelling speed. Designed for use of metalure inks.

Just like the high-gloss version of the source material for this grade, the embossed version is also one of the best label papers for high-quality printing standards and stringent labelling requirements.

Niklakett Premium Fashion is the paper for the offset printer, who will be highly delighted when multi-colour applications and captivating, vibrant colours are required. Of course, Niklakett Premium Fashion is excellent for punching and also for high-speed labelling.

It is the feel of Niklakett Medium Fashion that is different to the smooth, high-gloss source material. The textured surface keeps us looking for longer, radiating a balanced calm which is confirmed by touch. Marketing specialists in the drinks sector, which is where this paper is chiefly deployed, make use of this advantage so that there is a positive tactile feedback, especially when consuming the product.

Print Information

Very good results with all common printing processes, especially in combination with metal effect inks. Ink dries quickly

Varnishing

Universally varnishable.

Finishing

Suitable for foil and relief stamping. Excellent stamping quality even for demanding shapes (neck labels).

Labelling

Suitable for all common gluing systems. High labelling speed. Excellent glue consumption using functional coating on the reverse. Very good flatness characteristics. For one-way and returnable applications. The handling guidelines from the glue producer have to be followed to achieve optimum labelling results.

Special features

Particularly well suited for extremely tight radii. Outstanding ink retention in washing solution. Available in various embossing designs. According guideline 94/62/EG.

Service Information

Possibility for production min. 2-3 x/month

B&B has

ISO 9001, ISO 14001, HACCP and PEFC certification



property	unit	method		tolerance	
Substance	g/m ²	ISO 536		75	+/- 3%
Caliper	µm	ISO 534, single sheet measur.		74	+/- 5%
Brighthness	%	ISO 2470, R457 D65	CS	91	+/- 2
Opacity dry	%	ISO 2471		88	+/- 2
Opacity wet	%	According ISO 2471 5 minutes soaking time		73	- 2
Smoothness Bekk	Bekk sec.	ISO 5627	CS RS	< 100 < 100	guide number guide number
Cobb 60"	g/m ²	ISO 535	CS RS	17 13	+/- 4 +/- 3
Tensile strength dry	N/15m m	ISO 1924-2	MD CD	65 42	- 10 - 7
Tensile strength wet	N/15m m	ISO 3781 10 minutes soaking time	MD CD	14 12	- 2 - 2
Resistance to penetration and come-off time in alkaline solution	Second s	DIN 16524-6	PT COT	60 100	max. max.
Resistance to alkaline solution	Minutes	DIN 16524-7		60	min.
Climatic Curl 30 % relative Humidity				-1,50	guide number
Climatic Curl 50 % relative Humidity	cm	internal instruction QK/40		0	guide number
Climatic Curl 80 % relative Humidity				1,50	guide number
absolute Humidity	%	online-measurement on Kalander		4,7	+/- 0,5
relative Humidity	%	Hygromer Rotronic		50	+/- 5 at 23 °C

Key: CS - coated Side
RS - reverse Side
MD - Machine Direction

CD - Cross Direction
PT - penetration time
COT - come-off time

Testing conditions :
Standard climate EN 20187
23° Celsius, 50 % relative Feuchte

Date of issue : 03-2009

Label Management by B & B

All rights to improve quality due to technical modifications reserved